

WORK MATERIAL	CARBON STEELS		CARBON STEELS		CARBON STEELS		ALLOY STEELS		ALLOY STEELS		STAINLESS STEELS		TITANIUM ALLOYS	
	N	S	N	S	N	S	N	S	N	S	N	S	N	S
HARDNESS			~ HRC23		~ HRC23 ~ 28		HRC23 ~ 34		HRC34 ~ 38		HRC23			
STRENGTH	~ 570 N/mm <sup>2</sup>		~ 830 N/mm <sup>2</sup>		830 ~ 950 N/mm <sup>2</sup>		830 ~ 1110 N/mm <sup>2</sup>		1110 ~ 1260 N/mm <sup>2</sup>		830 N/mm <sup>2</sup>		410 N/mm <sup>2</sup>	
DRILLING SPEED	22 ~ 27 m/min		15 ~ 20 m/min		10 ~ 15 m/min		15 ~ 20 m/min		8 ~ 12 m/min		15 ~ 20 m/min		8 ~ 12 m/min	
DIAMETER	N	S	N	S	N	S	N	S	N	S	N	S	N	S
2.5	3380	0.025	2550	0.025	1900	0.015	2380	0.020	1400	0.015	2550	0.025	1400	0.020
3.0	2700	0.050	2000	0.050	1500	0.025	1880	0.050	1100	0.020	2000	0.050	1100	0.025
5.0	1700	0.063	1280	0.063	960	0.038	1190	0.063	700	0.025	1280	0.063	700	0.038
8.0	1050	0.130	780	0.130	590	0.076	730	0.130	430	0.038	780	0.130	430	0.076
11.0	750	0.150	560	0.150	425	0.076	520	0.180	310	0.050	560	0.150	430	0.076
19.0	440	0.230	330	0.230	255	0.130	300	0.230	180	0.050	330	0.230	180	0.130
31.0	260	0.280	195	0.280	145	0.180	180	0.280	107	0.076	195	0.280	107	0.180

WORK MATERIAL	TOOL STEELS		CAST IRON		ALUMINUM ALLOYS		MAGNESIUM ALLOYS		ZINC ALLOYS		PLASTICS	
	N	S	N	S	N	S	N	S	N	S	N	S
HARDNESS			~ HRC21									
STRENGTH	~ 270 N/mm <sup>2</sup>		~ 800 N/mm <sup>2</sup>									
DRILLING SPEED	20 ~ 25 m/min		15 ~ 20 m/min		45 ~ 50 m/min		55 ~ 65 m/min		40 ~ 50 m/min		20 ~ 25 m/min	
DIAMETER	N	S	N	S	N	S	N	S	N	S	N	S
2.5	3180	0.042	2250	0.025	6400	0.038	8600	0.038	6400	0.038	3380	0.025
3.0	2500	0.050	2000	0.050	5000	0.063	6800	0.063	5000	0.063	2700	0.050
5.0	1590	0.063	1280	0.063	3200	0.076	4300	0.076	3200	0.076	1700	0.063
8.0	970	0.130	780	0.130	2000	0.180	2600	0.180	2000	0.180	1050	0.130
11.0	700	0.180	560	0.150	1400	0.200	1900	0.200	1400	0.200	750	0.150
19.0	440	0.230	330	0.230	820	0.300	1100	0.300	820	0.300	440	0.230
31.0	240	0.300	195	0.280	490	0.380	660	0.380	490	0.380	260	0.280

N = R.P.M  
S = Feed per  
Revolution  
(mm/rev.)