



MATERIAL	CARBON STEELS ALLOY STEELS TOOL STEELS				CARBON STEELS ALLOY STEELS TOOL STEELS				HARDENED STEELS			
HARDNESS	~ HRc 30				HRc 30 ~ HRc 45				HRc 45 ~ HRc 50			
STRENGTH	~1000N/mm <sup>2</sup>				1000~1500N/mm <sup>2</sup>				1500N/mm <sup>2</sup> ~			
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
R1.0 × 2.0	12350	640	80	0.026	9150	415	55	0.023	4000	125	25	0.016
R1.5 × 3.0	11400	575	105	0.025	8550	390	80	0.023	3800	125	35	0.016
R2.0 × 4.0	8950	630	110	0.035	7150	450	90	0.031	3600	150	45	0.021
R2.5 × 5.0	7800	700	125	0.045	6200	490	95	0.040	3100	150	50	0.024
R3.0 × 6.0	7250	870	135	0.060	5900	705	110	0.060	2700	160	50	0.030
R4.0 × 8.0	6100	1090	155	0.089	4900	785	125	0.080	2050	190	50	0.046
R5.0 × 10.0	5450	1330	170	0.122	4350	870	135	0.100	1750	190	55	0.054
R6.0 × 12.0	4990	1500	190	0.150	3950	950	150	0.120	1500	210	55	0.070
R7.0 × 14.0	4530	1495	200	0.165	3600	925	160	0.128	1300	210	55	0.081
R8.0 × 16.0	4085	1470	205	0.180	3200	905	160	0.141	1150	210	60	0.091
R9.0 × 18.0	3800	1425	215	0.188	3000	890	170	0.148	1050	210	60	0.100
R10.0 × 20.0	3550	1425	225	0.201	2800	885	175	0.158	950	210	60	0.111

ap : D1~D6=0.2mm  
D8~D20=0.3mm  
ae : 0.2D



MATERIAL	CAST IRON				ALUMINUM ALLOYS			
HARDNESS								
STRENGTH								
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
R1.0 × 2.0	10500	220	65	0.010	30800	395	195	0.006
R1.5 × 3.0	7050	230	65	0.016	20500	395	195	0.010
R2.0 × 4.0	5150	285	65	0.028	15400	395	195	0.013
R2.5 × 5.0	4150	330	65	0.040	12100	470	190	0.019
R3.0 × 6.0	3400	360	65	0.053	10300	470	195	0.023
R4.0 × 8.0	2500	460	65	0.092	7900	540	200	0.034
R5.0 × 10.0	2050	460	65	0.112	6150	540	195	0.044
R6.0 × 12.0	1750	460	65	0.131	5150	630	195	0.061
R7.0 × 14.0	1400	460	60	0.164	4300	630	190	0.073
R8.0 × 16.0	1300	460	65	0.177	3850	540	195	0.070
R9.0 × 18.0	1100	460	60	0.209	3400	540	190	0.079
R10.0 × 20.0	1050	420	65	0.200	2950	540	185	0.092



※ The FEED, in long & extra long types, should be reduced by around 50%

RPM = rev./min.  
FEED = mm/min.  
Vc = m/min.  
fz = mm/t